

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
12 September 2003 (12.09.2003)

PCT

(10) International Publication Number
WO 03/074581 A1

(51) International Patent Classification⁷: **C08G 18/42**,
18/60, 18/80, 69/48, 63/91

(21) International Application Number: PCT/NL03/00133

(22) International Filing Date: 20 February 2003 (20.02.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
02075724.1 22 February 2002 (22.02.2002) EP

(71) Applicant (for all designated States except US): **DSM N.V.**
[NL/NL]; Het Overloon 1, NL-6411 TE Heerlen (NL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **LOONTJENS**,
Jacobus, Antonius [NL/NL]; Synagogeplantsoen 76,
NL-6231 KK Meerssen (NL). **PLUM, Bartholomeus**,
Johannes, Margretha [NL/NL]; Klein Berghemmerweg
52, NL-6235 AJ Ulestraten (NL).

(74) Agent: **MOOIJ, Hans**; DSM Patents & Trademarks, P.O.
Box 9, NL-6160 MA Geleen (NL).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE,
SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,
VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI,
SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN,
GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: PROCESS FOR PREPARING A HIGH-MOLECULAR POLYAMIDE, POLYESTER, COPOLYESTER, COPOLYAMIDE OR POLYESTER-AMIDE BLOCK COPOLYMER



(I)

(57) Abstract: The invention relates to a process for preparing a high-molecular polyamide or polyester or copolyester by melt-mixing polyamide or polyester or copolyester having a lower molecular weight with a blocked diisocyanate having the Formula (I), wherein R=linear, branched or cyclo aliphatic C₂-C₂₀ or aromatic C₆-C₂₀ and B₁, B₂=Caprolactam, Imidazole, dimethyl-pyrazole, triazole, oxim, malonic acid ester, ethylacetylacetonate, phenol, cresol, aliphatic alcohol, secondary amine, hydroxy benzoic acid methyl ester. With the process according to the invention a permanent increase in the molecular weight of a polyamide is obtained within 2 minutes, whereas this takes at least 10 minutes under comparable conditions using a blocked isocyanate according to the state of the art.

WO 03/074581 A1

5 PROCESS FOR PREPARING A HIGH-MOLECULAR POLYAMIDE, POLYESTER,
COPOLYESTER, COPOLYAMIDE OR POLYESTER-AMIDE BLOCK COPOLYMER


The invention relates to a process for preparing a high-molecular polyamide, polyester, copolyester, copolyamide or polyester-amide block copolymer by melt-mixing polyamide or polyester or copolyesters or a mixture or mixtures of a
10 polyamide and/or a polyester having a lower molecular weight, with a diisocyanate. Under high molecular polyamide, polyester, copolyester, copolyamide or polyester amide block copolymer is understood a polymer with a higher molecular weight than the respective polymer before melt mixing.

Such a process is for example known from DE 430663 A1, in which a
15 diisocyanate is used to increase the viscosity of polyamide-6. The diisocyanate used in the examples of DE 430663 A1 are generally 4,4'-diphenylmethanediisocyanate (MDI) or hexamethylenediisocyanate(HMDI).


Diisocyanates however have the drawback of leading to undesired side-reactions and discoloration of the polyamide, polyester, copolyester, copolyamide
20 or polyester-amide block copolymer. These side-reactions and discoloration effects of diisocyanate are extensively described by J.Kylmä, et. al. in Polymer 42 (2001)3333-3343, by B. Guo et. al. in Journal of Applied Polymer Science, Vol. 71, 1827-1834 (1999) and by N. Torres et. al. in Journal of Applied Polymer Science, Vol. 79, 1816-1824, (2001). As side reactions branching of the polymer can occur. A branched
25 polymer is undesirable for polymer processing, e.g. fibre spinning, as it reduces the drawability of the fibre and consequently reduces the attainable mechanical properties.

The invention's aim is hence to provide a process for preparing a high-molecular polyamide, polyester, copolyester or polyester-amide block copolymer that does not involve the above drawbacks.

30 The inventors have now most surprisingly found that when the polyamide, the polyester, copolyester or mixtures thereof having the lower molecular weight reacts in the melt with a blocked diisocyanate having the following formula



wherein R = linear, branched or cyclo aliphatic C₂-C₂₀ or aromatic C₆-C₂₀, for example:



5

and R₁, R₂, R₃, R₄, R₅ = Aliphatic C₁-C₁₀, chloro, bromo, fluoro and B₁, B₂ = caprolactam, imidazole, dimethyl-pyrazole, triazole, oxim, malonic acid ester, ethylacetylacetonate, phenol, cresol, aliphatic alcohol, secondary amine, hydroxy benzoic acid methyl ester.

10

With the process of the invention, a colorless, stable linear polyamide or polyester or copolyester with increased molecular mass is very quickly obtained. Phenylene bisoxazoline or oxazine gives an additional increase in the molecular weight when used next to the blocked isocyanate. The use of phenylene bisoxazoline or oxazine is optional.

15

'Blocked diisocyanate' is understood to be a compound having the formula as given in appendix 1:

Blocked diisocyanates are commercially available from Bayer, Dai Nippon Ink, Nippon Polyurethanes, Asahi, Takeda, Rhodia, Baxenden and Creanova.

20

The amount of blocked diisocyanate used in the process, according

to the invention, may vary within a wide range. Usually at least about 0.1 wt.%, relative to the polyamide or the polyester or the copolyesters, will be required to obtain an appreciable effect. Amounts of more than 4 wt.% result only in higher costs.

5 Usually a person skilled in the art will adjust the amount of blocked diisocyanate to be used to the number of amino or hydroxyl end groups available and the increase in viscosity to be realized as a result of the increased molecular weight. He will usually determine the optimum amount for his situation through simple experimentation.

10 In principle, the process of the invention can be used for all types of polyamides and polyesters. The polyamides include at least the aliphatic polyamides, for example polyamide-4, polyamide-6, polyamide-8, polyamide-4,6, polyamide-6,6, polyamide-6,10, polyamides derived from an aliphatic diamine and an aromatic dicarboxylic acid, for example polyamide-4,T, polyamide-6,T, polyamide-4,I, in which T stands for terephthalate and I for isophthalate, copolyamides of linear polyamides and
15 copolyamides of an aliphatic and a partially aromatic polyamide, for example 6/6,T, 6/6,6/6,T.

The polyesters include at least polyesters derived from aliphatic dicarboxylic acids and diols, polyesters from aliphatic diols and aromatic dicarboxylic acids, copolyesters that are partially aliphatic and partially aromatic and polyesters that
20 contain units derived from cycloaliphatic dicarboxylic acids and diols. Specific examples are polybutylene adipate, polyethylene terephthalate, polyethylene naphthalate, polybutyleneterephthalate, polypropyleneterephthalate, copolyesters of polybutyleneadipate and polybutyleneterephthalate, the polyester derived from butanediol and cyclohexane dicarboxylic acid.

25 The copolyesters include at least polyesters derived from aliphatic dicarboxylic acids and diols, polyesters from aliphatic diols and aromatic dicarboxylic acids, copolyesters that are partially aliphatic and partially aromatic and polyesters that contain units derived from cycloaliphatic dicarboxylic acids and diols. Specific examples are polybutylene adipate, polyethylene terephthalate, polyethylene
30 naphthalate, polybutyleneterephthalate, copolyesters of polybutyleneadipate and polybutyleneterephthalate, the polyester derived from butanediol and cyclohexane dicarboxylic acid and polyethers as polyoxytetramethylene, polypropylene glycol, polyethylene glycol and copolyethers of ethylene oxide and propylene oxide, Jeffamines, amino terminal acrylonitril-butadiene copolymers.

35 Mixtures of polyesters and/or polyamides are included in the process

of the invention as well. This makes it possible to produce a copolymer, starting from homopolymers and the blocked isocyanate. Furthermore it is possible to add hydroxy- or amine functional additives in the process of the invention. An example of a hydroxy functional additive is polyoxytetramethylene or the corresponding oligomer.

5 The process according to the invention can be carried out in a simple manner using the usual melt-mixing techniques and equipment, for example by dry blending the polyamide or polyester having a lower molecular weight and the blocked diisocyanate and optionally also other additives in a solid state, for example in a
10 tumbler drier, after which the mixture obtained is melted in a usual melt-mixing apparatus, for example a Haake kneader, a Brabender mixer or a single- or twin-screw extruder. The different components can also be fed to the mixing apparatus separately.

Best results are obtained if the lower molecular polyamide or polyester are thoroughly dried.

 The blocked diisocyanate can also be added to the melted polyamide
15 or polyester product stream in the polymerisation process as it leaves the polymerization reactor. The polymerization process can be carried out both batchwise or in a continuous mode. In the first case a reduction of the residence time in the reactor can be realized and thus an increase in productivity; with the continuous process the post-condensation step, that is usually necessary to obtain a polyamide or
20 polyester of sufficient molecular weight, can be avoided.

 The molecular weight of the polyamide or polyester having the lower molecular weight may vary over a wide range and is mainly determined by economical reasons and the source of the material. In general it may vary from about 1000 to about 20.000 g/mol expressed as number averaged molecular weight M_n . However situations
25 are possible in which a mixture containing a polyamide or polyester of high molecular weight for instance 25.000 g/mol and an appreciable fraction oligomeric polyamide or polyester of molecular weight less than 1000 g/mol is reacted in the melt with the blocked isocyanate according to the present invention.

 The molecular weight of the high molecular weight polyamide or
30 polyester to be produced by the process of the invention can be freely chosen and generally is higher than 15.000, preferably higher than 20.000, even more preferably higher than 25.000 g/mol.

 The polyamide or polyester obtained by the process of the invention can be processed into shaped parts by injection or blow moulding, extrusion or melt
35 spinning to obtain moulded articles, films and semi-shaped products as e.g. stock

shapes and fibres, respectively.

The invention will now be elucidated with reference to the following examples, without however being limited thereto.

5 Example 1 and 2; Comparative experiment 1.

Materials used:

a. polyamide-6 having a $\eta_{rel} = 2.56$ measured in formic acid and a concentration of end groups $-COOH = 0.052$ meq/g $-NH_2 = 0.052$ meq/g.

b. Caprolactam blocked diisocyanate of hexamethylene diisocyanate: 'Blocked HDI'

10 Nylon-6 was grinded and dried over night at $100^{\circ}C$, in nitrogen under vacuum. The blocked diisocyanate was dissolved in chloroform and mixed with the polymer to achieve a homogeneous mixture. This mixture was dried at $50^{\circ}C$ in nitrogen over night. The mixture was molten in a DSM midi extruder (15 g), at $240^{\circ}C$ until a constant torque of the screw was obtained and the mixing was continued during 4
15 minutes. The torque was measured at different times. The mixing was carried out under a nitrogen blanket to prevent the risk of the polyamide decomposing as a result of oxidation.

Table 1 shows the compositions investigated and the results of the measurements.

20

Table 1

Measurement	Comparative Experiment 1	Example 1	Example 2
	Blank	1 eq Blocked HDI*	2 eq Blocked HDI*
RPM	80	80	80
Mixing time, Total residence time in midi extruder	40" 4'40'	45" 4'45"	45" 4'45"
η_{rel}	2,34	2,93	3,38
Melt viscosity at ω = 1 rad/s in Pa.s	550	1500	3500

* One and two mol blocked isocyanate groups per mol amine end group of nylon-6.

The results of Experiments 1 and 2 show the surprisingly high activity of the blocked diisocyanate, as a result of which a stable high value of the melt viscosity (which was monitored through the torque of the midi extruder) was obtained after 2 minutes already, whereas this is not the case when no use is made of the blocked diisocyanate. Furthermore melt viscosity measurements, as given in table 1, were done through Dynamic Mechanical Spectroscopy (DMS). This technique not only gives information regarding the viscosity of a polymer melt, but also whether branching of a polymer has occurred. According to the DMS measurements the products of experiment 1 and 2 were strictly linear, no indication for branching was found.


Thanks to this short reaction time, which is of the same order as the residence time in a normal extrusion, e.g. in a commercial polymer production plant, a stable, increased melt viscosity can be realized in practice.

The relative viscosity, η_{rel} , is a measure for the molecular weight of a polymer. For determining the relative viscosity the polymer is dissolved in a solvent and the obtained solution is passed through an Übbelohde capillary viscosimeter. The time, t , for a given volume of solution to pass through the Übbelohde capillary is measured and compared with the time, t_0 , for the same volume of solvent to pass through the Übbelohde capillary. The ratio t/t_0 is referred to as the relative viscosity. For the polyamide the relative viscosity was measured in a solution of 1 gram polyamide in 100 ml of 90 wt.% formic acid at a temperature of 25 °C. Übbelohde capillaries were used in accordance with ISO307.

The melt viscosity was measured at 230 °C on an ARES DMS equipment.

CLAIMS

1. Process for preparing a high-molecular polyamide, polyester, copolyester, copolyamide or polyester-amide block copolymer by melt-mixing a polyamide, a polyester, copolyesters or a mixture or mixtures of a polyamide and/or a polyester having a lower molecular weight, than the polymer obtained with the process of the invention, with an diisocyanate, characterized in that the diisocyanate is a blocked diisocyanate having following the formula,



10

wherein R = linear, branched or cyclo aliphatic C₂-C₂₀ or aromatic C₆-C₂₀ and B₁, B₂ = caprolactam, imidazole, dimethyl-pyrazole, triazole, oxim, malonic acid ester, ethylacetylacetonate, phenol, cresol, aliphatic alcohol, secondary amine, hydroxy benzoic acid methyl ester.

15

2. Process according to Claim 1, characterized in that use is made of 0.05 to 4 wt.% of the blocked diisocyanate, relative to the polyamide, the polyester, the copolyester or the mixture or both.
3. Process of any one of claims 1-2, wherein the melt mixing is done in an extruder.
4. Process of claim 3 wherein the extruder is a twin-screw extruder.

20

INTERNATIONAL SEARCH REPORT

International Application No
PCT/NL 03/00133

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08G18/42 C08G18/60 C08G18/80 C08G69/48 C08G63/91

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

WPI Data, PAJ, EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE 44 30 663 A (THUERINGISCHES INST TEXTIL) 7 March 1996 (1996-03-07) cited in the application claims 1,2	1-4
A	US 4 689 361 A (MUMCU SALIH ET AL) 25 August 1987 (1987-08-25) claim 1; example 1	1-4



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the International filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- * & * document member of the same patent family

Date of the actual completion of the international search

24 April 2003

Date of mailing of the international search report

07/05/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Hoffmann, K

INTERNATIONAL SEARCH REPORT

International Application No
PCT/NL 03/00133

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
DE 4430663	A	07-03-1996	DE	4430663 A1	07-03-1996
US 4689361	A	25-08-1987	DE	3510688 A1	25-09-1986
			AT	48627 T	15-12-1989
			AU	566063 B2	08-10-1987
			AU	5500286 A	25-09-1986
			CA	1244991 A1	15-11-1988
			DE	3667483 D1	18-01-1990
			EP	0199000 A2	29-10-1986
			JP	1041182 B	04-09-1989
			JP	1556140 C	23-04-1990
			JP	61221275 A	01-10-1986